

TYPICAL PHYSICAL PROPERTIES

COLOR	Multi-color
Coverage Rate	80-100 sf/gal
FLASHPOINT	101°F
WEIGHT (LB./GAL.)	
SOLIDS (% BY WEIGHT).	50.0±1%
VISCOSITY @ 78°	2900 CPS
DRYING TIME	2 – 4 Hours
ELONGATION	.ASTM-D 412500%
TENSILE STRENGTH	ASTM-D 4121520 PSI
PERMEANCE (10MILS)	0.166 perms
FUNGI RESISTANCE	0 (pass)
WATER SWELL	0%
WEATHERING	PASS
LOW TEMP. FLEX	.ASTM-D 52PASS
WIND DRIVEN RAIN	.тт-с-555враss

WET ADHESION (ASTM C 794/D 903)

METAL	. PASS
SBS MOD. BIT	. PASS
APP Mod. Bit	. PASS
SMOOTH BUR	. PASS
EPDM	. PASS
ТРО	. PASS
HYPALON	. PASS
SPUF (FOAM)	. PASS

<u>Recommended Spray Equipment = Airless</u>				
TIP SIZE	0.025"			
FLUID PRESSURE (PSI)				
Fluid Hose Size	3/8"-1/2"			

ALDOCOAT 900 PREMIUM RUBBER ROOF COATING

PRODUCT DESCRIPTION

ALDOCOAT 900 Premium Rubber Roof Coating is a unique Elastomeric Rubber Coating that provides extremely effective protection against weather extremes and ultraviolet exposure. This Premium Rubber Roof Coating will control corrosion and rust bleed through, reducing the need for costly re-applications. It is a one-component product with Class A Fire Rating that will form a seamless membrane over properly prepared surfaces.

Available in 12 standard colors. Custom colors available with 100 gallon minimum.

White	Off White	Light Gray	Gray	Black	Light Beige
Beige	Light Green	Forest Green	Light Blue	Tile Red	French Press

*Due to monitor & print settings, actual colors may vary. Please contact us for color samples if you need help selecting a coating.

GENERAL SURFACE PREP

ALDOCOAT 900 may be applied by medium nap rollers, soft brushes or conventional airless spray equipment. The surface must be free of any oils, moisture, rust scale, soil or other contaminates that may interfere with good adhesion. Remove any loose material from seams or other surfaces with a wire brush or scraper. Oil and grease should also be removed with solvents or an appropriate detergent cleaner. In many cases high pressure water blast will be sufficient to prepare the surface.

For best results, apply ALDOCOAT 900 when ambient air and the substrate is within $50 - 100^{\circ}$ F. For best spray application, the product should be at a minimum of 60° F. Lower temperatures can be utilized for brush.

LIMITATIONS AND PRECAUTIONS

AVOID MOISTURE CONTAMINATION IN SEALED CONTAINERS. Store in a dry environment at temperatures between 40°F - 85°F. KEEP AWAY FROM HEAT, OPEN FLAME OR SPARKS. USE ONLY IN WELL VENTILATED AREAS WITH PROPER PROTECTIVE EQUIPMENT. Avoid breathing vapor or mist.